



ITCOGEL LF 21

ITCOGEL LF 21 Tube Filling Compound (Thixotropic Jelly) is a soft, non-melting, white opaque, water barrier compound. It is based on synthetic and aliphatic hydrocarbons and has been formulated for use in filling, buffering, of loose tube in speciality designs of Optical Fibre Cables.

ITCOGEL LF 21 is a speciality gel with very low density and light weight. It gives additional advantage of high line - speed processing and reduction in weight of cable. It also exhibits good stability over a wide temperature range of - 40°C to + 80°C.

Appearance	Opaque White Gel without visible impurities	Visual (Erichsen Gauge 100 μ)
Flash Point COC - °C	> 230	ASTM D 92
Drop Point - °C	> 200	ASTM D 566
Viscosity at 25°C, 100 rpm - cps	41000 ± 5000	Brookfield Viscometer HADV, Spindle No. 7
Cone Penetration - 1/10 mm at + 25°C at - 40°C	≥ 370 > 200	ASTM D 937
Density at 25°C - g/cm ³	0.45 ± 0.02	ASTM D 1217
Volatility, 24 hrs at 100°C - %	< 1	FTM 791 C
Oil Separation, 24 hrs at 100°C - %	Zero	FTM 791 C
Oxidation Induction Time, 190°C, Alu. Pan - minutes	> 30	ASTM D 3895

Packing In metal drums with epoxy lining: Height – 885 mm, Internal Diameter – 570 mm, 90 Kg Nett weight. Bulk Bag (Fluid Bag) packing also available on request.

Storage Minimum 3 years in original packed condition stored at room temperature.

Safety As per our knowledge and available information, ITCOGEL LF 21 does not pose any health hazard. For further information, please refer to MSDS a copy of which is available upon request.

Compatibility Information regarding compatibility of this product with associated cable materials is available upon request.

Itco Industries Limited

ITCOGEL™

321, Raheja Arcade, Koramangala, Bangalore 560 095 India

Information provided in this Data Sheet is based on our knowledge and experience and is meant for general guidance only, without guarantee or representation as to results. Suitability of the product for an intended use shall be the sole responsibility of the user. We reserve the right to modify the above specified values without notice. For further information regarding material specification and / or application conditions, please contact ITCO Industries Limited.